



中国认可
国际互认
检测
TESTING
CNAS L15253

检验报告 TEST REPORT

样品名称: 无醛刨花板

Sample Description

商标/型号: ——/——

Brand/Model

委托单位: 雅安市汇龙环保新材料有限公司

Authorized By

生产单位: ——

Manufacturer

检验类别: 委托检验

Test Type

报告日期: 二〇二五年四月十五日

Tested Date



扫描验证真伪

检验报告编号: SCF-WT-SC-25032132-01



说明

STATEMENTS

1. 赛德检测是首个家具行业公共技术测试平台，具有检验检测机构资质认定CMA、实验室认可CNAS、美国消费品委员会CPSC认可、中国质量认证签约实验室、环境标志签约实验室等多项权威资质认可。提供家具成品及原辅材料、家居建材以及室内空气等领域的力学安全性能、理化性能、环保性能检测服务，为家具产品设计研发、生产制造、销售服务提供全过程的品质技术支持。

Saide Testing is the first public technology testing platform for the furniture industry with a number of authoritative qualifications such as CMA, CNAS, CPSC, CQC and China Environmental Labelling, providing professional devices and skills including mechanical property, physical and chemical property, chemical property for furniture, materials, building materials and air monitoring. And also, ST is trying to support the whole process of design, manufacture, development and sales service for furniture industry with quality service.

2. 本检测报告未加盖ST“检验检测专用章”无效，报告应加盖骑缝章。

The report is invalid without special seal for inspection of ST.

3. 本检测报告未经主检人、审核人、批准人签名无效。

The report is invalid without signatures of operator, inspector and apporover.

4. 本检测报告全部或部分复制、私自转让、盗用、冒用、涂改或以其他任何形式篡改的均属无效。

Any unauthorized reproduce in full or part, piracy, ralteration, forgery or falsification of the content is unlawful.

5. 对本检测报告若有异议，应于收到报告之日起十个工作日内向本检测单位提出，逾期不予受理。

Complaints should be made within 10 working days after receiving the testing report.

Any complaints made after this period will not be considered or accepted.

6. 本检测单位保证检测的客观公正性，对委托单位的商业信息、技术文件、检测报告等商业秘密履行保密义务。

ST assures objectivity and justness of the test, and fulfills the duty of confidentiality for appplicant's commercial information, technique document, and analysis report.

检验报告

TEST REPORT

编号： SCF-WT-SC-25032132-01

第 1 页 共 3 页


委托单位： 雅安市汇龙环保新材料有限公司
单位地址： 四川省雅安市经济开发区永兴大道
生产单位： ——
样品信息：

样品名称	商标/系列	型号/规格	生产日期/批号	数量
无醛刨花板	——/——	——/（600*600*18） mm	——/——	6块

样品状态： 完好
检验类型： 委托检验
收样日期： 2025年3月21日
样品编号： SC-25032132-01
验讫日期： 2025年4月15日
检验依据： GB/T 4897-2015 《刨花板》
GB/T 39600-2021 《人造板及其制品甲醛释放量分级》
检验结果： 详见第2～3页。
样品图片：



样品包装



样品正面

批准：

张旭

审核：

王林

主检：

李小成

检 验 报 告

TEST REPORT

编号： SCF-WT-SC-25032132-01

第 2 页 共 3 页

测试项目	标准要求		单位	实测结果	评定
板内密度偏差 (GB/T 4897-2015)	± 10.0		%	-2.7~+3.4	符合
含水率 (GB/T 4897-2015)	3~13		%	6.2	符合
静曲强度 (MOR) (GB/T 4897-2015)	≥ 11.0		MPa	12.7	符合
弹性模量 (MOE) (GB/T 4897-2015)	≥ 1600		MPa	2052	符合
内胶合强度 (GB/T 4897-2015)	≥ 0.35		MPa	0.55	符合
表面胶合强度 (GB/T 4897-2015)	≥ 0.8		MPa	1.4	符合
2h吸水厚度膨胀率 (GB/T 4897-2015)	≤ 8.0		%	1.0	符合
握螺钉力 (GB/T 4897-2015)	板面	≥ 900	N	1340	符合
	板边	≥ 600	N	1140	符合
甲醛释放量 (GB/T 39600-2021)	$E_1 \leq 0.124$ $E_0 \leq 0.050$ $E_{NF} \leq 0.025$		mg/m ³	0.022	符合 E ₀ 级 要求
说明	1. 板材类型为干燥状态下使用的家具型刨花板；（板材类型由委托方指定） 2. 项目“甲醛释放量”试验方法按照GB/T 17657-2013规定进行，该试验方法已过期，仅限特定产品标准（GB/T 39600-2021）引用时使用； 3. 所检样品的甲醛释放量达到稳定状态的测试时间为48h； 4. 送检样品基本信息由委托单位提供（实验室对此真实性不负任何责任）； 5. 以上检测结果仅适用于本实验室收到的样品。				


检 验 报 告

TEST REPORT

编号: SCF-WT-SC-25032132-01

第 3 页 共 3 页

附测试图片:



样品侧面

* * * * *

报告结束

